








## 1 - APPLICATION

	 WEIGHT		
10°C	<b>100:3</b>	7'	30'
20°C		5,5'	20'
30°C		4'	15'

## 2 - SANDING

 TIME
5 min
DISTANCE
80 cm
MAX. T
80°C

		 ORBIT		
INITIAL		7 – 5 mm	P150	P100
FINAL		5 – 3 mm		P180

## REMARKS

Do not add more hardener than specified. Mix thoroughly.  
It must be isolated before applying finish coating.  
Polyester putties will not harden at temperatures under +5°C.

## EQUIPMENT CLEANING

Clean putty knives with a cleaning thinner before the product hardens.

## SAFETY

Follow instructions of product label. For more information check the Safety Data Sheet.  
Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

## STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

## GUARANTEE

In unopened original packaging, one year from manufacturing date.

### SUGGESTION:

Futura Glass is ideal as a filling putty for the Tunning sector since its first low specific weight adds little weight to the vehicle.

For any technical information contact with our Customer Attention Service or our Technical Department.  
ROBERLO SA declines any responsibility due to an incorrect use of the product.