



PRIMANYL 2120

C29

VERSION: 250423

WASH PRIMER

DEFINITION

PRIMANYL 2120 is a multifunctional primer with two distinct functions: to ensure good adhesion and to protect metal from corrosion.

PRIMANYL 2120 is a chromate and lead-free product.

Due to its excellent adhesion, it is recommended for use in painting cycles of galvanized and aluminium surfaces.



Refinishing with 2k primers and any type of enamels except nitro synthetics, chlorinated rubber and epoxy.

The application of polyester putty on this product is not recommended.




PHYSICAL CHARACTERISTICS

Nature:	Modified vinyl	
Colour:	White, Green	
Appearance:	Matt	
Specific weight:	1.0-1.1 kg/l at 20°C.	
Dry film thickness:	10 microns	1 coat
VOC:	710 g/l	Application 2004/42/EC - IIB (c)(780)(710)
Yield:	12-14 m ² /l	10 microns








SURFACE OR SUBSTRATE PREPARATION

PROCESS		Aluminium	Steel	Galvanized	OEM paint
	P240	√	√	√	√
	DA93	√	√	√	√





MIXING RATIO

PRIMANYL 2120			
	1:1 Volume		
Hardener 2120	100:80 Weight	20"-24" F/4 at 20°C	8h

APPLICATION METHOD

	 mm	 bar	 cm		
	1,3-1,5	3	15 - 20	1	5'
 HVLP	1,3-1,5	2	10	1	5'

DRYING

			
20°C	5'	10'	30'

CLEANING OF THE EQUIPMENT

Clean with cleaning thinner before the product hardens.

SAFETY

Refer to the product label. For further information see safety data sheet.
Comply with the health and safety at work and waste disposal regulations.

STORAGE

Keep in a cool and ventilated place, avoiding direct exposure to sunlight. Store between +5°C and +30°C.

SHELF LIFE

One year in unopened original packaging.

These products are for professional use only. The Safety Data Sheet must be consulted before use and the precautionary warnings on the product packaging must be observed. Their correct use, in accordance with their purpose and respecting the technical and safety data provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO S.A.U. declines any responsibility due to the incorrect use of any product.

The information contained in this documentation is based on our scientific and technical knowledge at the date of issue. ROBERLO reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the responsibility of the user to verify that the information is up to date. The latest version of this document supersedes all previous versions.

All clauses included in this document are applicable to any future changes or modifications. For any further technical information, please contact our Customer Service or Technical Department.

TIP:

Primanyl 2120 acts on galvanized as an adhesion promoter and on bare sheet metal as an adhesion promoter and anticorrosive.