



AIRCOLOR ZINC PRIMER SPRAY

H44

VERSION: 201221
Pág:1/2

PRIMER SPRAY 1K

DEFINITION

Zinc spray. 99% purity of zinc content. Prevents corrosion of iron and steel, e.g. car bodies, exhaust pipes, doors, machines, fittings, gates, etc. The zinc layer forms a film that provides maximum protection against corrosion. Due to its good conductivity, it is very suitable for welding processes. Heat resistant up to 350°C.

PHYSICAL CHARACTERISTICS

Nature:	Epoxyester		
Color:	Zinc Matt		
Specific gravity:	1,2 kg/l at 20°C		
Propellant:	Dimethyl Ether		
Dry film thickness:	90 microns	4-5 layers	
Yield:	2m² per aerosol 400ml		
VOC:	638 g/l	Application	2004/42/EC - IIB (e)(840)(638)

SURFACE OR SUPPORT PREPARATION

PROCESS		Steel	Electrozinc-coated
	P80	✓	✓
	P150	✓	✓
	DA93	✓	✓

APPLICATION METHOD

1'	25-30 cm	4-5 layers (90 microns)

DRYING

20°C	10'	20'-30'	24h

OBSERVATIONS

Shake the aerosol well before use, approximately one minute after hearing the sound of the mixer.


Apply on clean and dry surfaces. Remove corrosion with a wire brush.

During application, it is recommended to shake the can periodically.

If the nozzle becomes blocked, replace it with a new one.

Never apply to equipment that is plugged in and use in well ventilated areas.

EQUIPMENT CLEANING



SAFETY

Consult the product label. For more information, consult the safety data sheet. Respect the health and safety guidelines at work, as well as those for waste disposal.

STORAGE

Keep in a cool and ventilated place avoiding direct exposure to sunlight. Store between + 5°C and + 30°C.

WARRANTY

One year in unopened original packaging.

These products are for professional use only. The Safety Data Sheet should be consulted before use and the precautionary warnings on the product packaging should be observed. Its correct use, according to its purpose and respecting its technical and security data, provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO S.A.U declines any liability due to the incorrect use of any product.

The information included in this documentation is based on our scientific and technical knowledge on the date of its issuance. ROBERLO S.A.U reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the user's responsibility to verify the update of the information. The latest version of this document replaces all previous versions.

All clauses contained herein apply to any future changes or modifications.

For any additional technical information please consult with our Customer Service or our Technical Department.