



# AIRCOLOR KLAREX clear coat gloss 2k

## H33

VERSION: 240223  
Page: 1/2

### 2K VARNISH

#### DEFINITION

2K varnish available in two gloss levels (matt and glossy). Developed for the process of repairing small damages or complete painting of assembly parts.

#### PHYSICAL CHARACTERISTICS

<b>Nature:</b>	Acrylic resin of 2 components
<b>Propellant:</b>	DME
<b>Colour:</b>	transparent
<b>Specific weight:</b>	0,908g/ml matt 0,898g/ml brilliant
<b>Shine (85°):</b>	12±3 matt 88±4 brilliant
<b>Dry film thickness:</b>	40µm
<b>Resistance of the varnish to heat:</b>	60 - 80 °C (long exposure) 110 - 120 °C (short exposure)
<b>Aerosol pressure (20°C):</b>	3,8-4,2 bar
<b>VOC:</b>	648 g/l matt 673 g/l brilliant
<b>PWR:</b>	Category: CCP Category limit: 1.5

#### SURFACE PREPARATION

30 minutes flash off is required between the basecoat and AIRCOLOR KLAREX clear coat gloss 2k application.

#### APPLICATION


2'			2'	15-20 cm	1-2 coats 40 µ	10-15'

#### DRYING TIMES

20°C	12'	80'	24h	24h	15'

**REMARKS**

Shake the aerosol before use for 2 minutes after hearing the sound of steel mixing balls.  
Protect the areas that do not need to be painted.  
Drying time depends on temperature, humidity as well as the film thickness applied.  
Pot life 24h at an ambient temperature of 68 ° F (20 ° C) and a relative humidity of approx. 40-50%.

**EQUIPMENT CLEANING****SAFETY**

Follow instructions on the product label. For more information check the Safety Data Sheet.  
Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

**STORAGE**

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

**SHELF LIFE**

One year in unopened original packaging.

These products are for professional use only. The Safety Data Sheet should be consulted before use and the precautionary warnings on the product packaging should be observed. Its correct use, according to its purpose and respecting its technical and security data, provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO S.A.U declines any liability due to the incorrect use of any product.

The information included in this documentation is based on our scientific and technical knowledge on the date of its issuance. ROBERLO S.A.U reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the user's responsibility to verify the update of the information. The latest version of this document replaces all previous versions.

All clauses contained herein apply to any future changes or modifications.  
For any additional technical information please consult with our Customer Service or our Technical Department.